



Standard Test Method for Stability of Water-in-Oil Emulsions Under Low to Ambient Temperature Cycling Conditions¹

This standard is issued under the fixed designation D3709; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the indication of the stability of water-in-oil emulsions when subjected to temperature cycling changes between ambient temperature and -18°C (0°F).

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

D1744 Test Method for Water in Liquid Petroleum Products by Karl Fischer Reagent²

3. Summary of Test Method

3.1 A 100-mL sample contained in a graduated 100-mL cylinder is placed in a cooling box at -18°C (0°F) for 16 h and then allowed to stand at room temperature for 8 h. This cycling procedure is repeated to give a total of nine cycles, except that the fifth cycle is one of 64 h at -18°C (0°F), 8 h at room temperature. At the completion of the cycling procedure the sample is examined for the amount of free oil and free water separated. In addition, water contents of the sample at specified levels in the upper and lower layers of the sample are also obtained.

4. Significance and Use

4.1 This test method indicates the ability of the emulsion to withstand mild to moderately severe winter conditions of use

and storage. Generally this significance would be limited to conditions where the emulsion reaches a minimum temperature of -18°C (0°F).

5. Apparatus

5.1 *Cold Box*—A thermostatically controlled freezer or cold box capable of being maintained at $-18 \pm 1.5^{\circ}\text{C}$ ($0 \pm 3^{\circ}\text{F}$).

5.2 *Graduated Cylinder*—A stoppered 100-mL glass cylinder graduated in 1.0-mL increments. The stopper should have a vent groove to prevent vacuum or pressure build-up during the test.

5.3 *Pipet*, 10-mL glass.

5.4 *Microsyringe*, 0.05-mL glass with a fixed needle, No. 19 gage, point style No. 3.

5.5 *Glass Vials*, approximately 30-mL size.

6. Preparation of Sample

6.1 To ensure uniformity of the sample, it should be mixed thoroughly before removing the quantity required for the test. Vigorous hand shaking or mechanical mixing for 3 to 5 min is recommended for litre-size containers or less.

6.2 Special difficulties arise in mixing and withdrawing representative samples from large containers. This is due to the nature of water-in-oil emulsions that are two-phase systems as distinct from truly homogeneous systems. Vigorous mechanical stirring for an extended period is the best means of achieving homogeneity. However, for unstable emulsions that have been in storage for some time there is no satisfactory way to obtain a representative sample.

7. Procedure

7.1 After careful preparation of the sample to ensure homogeneity (described in Section 6), transfer 100 mL to a graduated 100-mL cylinder. Insert the vented stopper.

7.2 Place the cylinder in the cold box at $-18 \pm 1.5^{\circ}\text{C}$ ($0 \pm 3^{\circ}\text{F}$) for a period of 16 h. Withdraw the cylinder from the cold box and allow to stand at room temperature, $21 \pm 3^{\circ}\text{C}$ ($70 \pm 5^{\circ}\text{F}$), for a period of 8 h.

7.3 Repeat the cycling procedure as in 7.2 for three more cycles.

7.4 Replace the cylinder in the cold box for a period of 64 h. Withdraw and allow to stand at room temperature for 8 h.

¹ This test method is under the jurisdiction of ASTM Committee D02 on Petroleum Products and Lubricants and is the direct responsibility of Subcommittee D02.N0.02 on Industrial Applications.

Current edition approved Oct. 1, 2010. Published November 2010. Originally approved in 1978. Last previous edition approved in 1989 as D3709-89(2005) ^{e1}. DOI: 10.1520/D3709-89R10.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

7.5 Repeat the cycling procedure as in 7.2 for four more cycles, except that during the final cycle, the period at room temperature is limited to 3 h instead of 8 h before making observations.

7.6 Observe and record the following:

7.6.1 The amount of oil separated, percent volume, and

7.6.2 The amount of water separated, percent volume.

7.7 By means of a 10-mL pipet, withdraw aliquots in the following order.

7.7.1 With the pipet tip located exactly at the 80-mL mark, slowly withdraw a 10-mL sample and transfer to a small glass vial. This is designated as the upper layer sample.

7.7.2 With the pipet tip located exactly at the 15-mL mark, slowly withdraw a 10-mL sample and transfer to a small glass vial. This is designated as the lower layer sample.

7.8 Determine the water content, as percent weight, of the upper layer and lower layer samples, after shaking, by the procedure given in the Annex. Use a 0.05-mL sample transferred from the vials by means of a glass microsyringe.

8. Report

8.1 Report the results as follows:

8.1.1 Oil separation, percent volume,

8.1.2 Water separation, percent volume,

8.1.3 Upper layer water content, percent weight, and

8.1.4 Lower layer water content, percent weight.

9. Precision and Bias ³

9.1 The precision (see [Note 1](#)) of this test method is dependent on the degree of instability brought about by the temperature cycling process.

9.1.1 *Type I—Stable Emulsions (Procedures A and B):*

³ Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:D02-1158.

9.1.1.1 *Precision*—The precision of the method as determined by the statistical examination of interlaboratory test results is as follows.

9.1.1.2 *Repeatability*—The difference between successive results obtained by the same operator with the same apparatus under constant operating conditions on identical test material would, in the long run, in the normal and correct operation of the test method, exceed the following values only in one case in twenty. (See [Table 1](#).)

9.1.1.3 *Reproducibility*—The difference between two single and independent results obtained by different operators working in different laboratories on identical test material would, in the long run, exceed the following values only in one case in twenty. (See [Table 1](#).)

NOTE 1—Precision limits are based on a round-robin test program carried out in Technical Division N in 1977 using invert emulsion samples with water contents between 35 and 50 % (weight). Eleven cooperators tested five samples representing highly stable, borderline, and unstable emulsions.

9.1.2 *Type II—Unstable Emulsions*—Results can vary widely on samples which show any degree of instability brought about by temperature cycling and no precision limits can be set.

9.1.3 *Bias*—No bias statement is possible because there is no absolute value. The results are interpretable only with respect to this test.

10. Keywords

10.1 emulsions; oil separation; water separation

TABLE 1 Repeatability and Reproducibility For Type 1 Only

	Free Oil, %	Free Water, %	Difference in % Water Content Upper Layer Versus Lower Layer
Repeatability	1	1	3
Reproducibility	2	2	3

ANNEX

(Mandatory Information)

A1. MODIFIED TEST METHOD D1744 (KARL FISCHER)

A1.1 Scope

A1.1.1 This test method covers the determination of water in the concentration from 50 to 1000 ppm in liquid petroleum products.

A1.2 Significance and Use

A1.2.1 Knowledge of the water content of petroleum products can be useful to predict quality and performance characteristics of the product.

A1.3 Modified Procedure

A1.3.1 To obtain weight of sample, weigh the syringe to 0.1 mg before and after introducing the sample to the titration vessel.

A1.3.2 Use a 1 part xylene to 2 parts methanol mix as the solvent instead of a 3 parts chloroform to 1 part methanol mix. (**Warning**—Flammable. Harmful if inhaled. Skin irritant on repeated contact. Eye irritant. Aspiration hazard.)

A1.3.3 A water equivalent of 2.0 to 2.5 mg of water/mL for the Karl Fischer reagent is recommended.

A1.4 Precision and Bias

A1.4.1 The precision of Test Method [D1744](#) with this solvent system is now under study by Subcommittee D02.03.

A1.4.2 No bias statement is possible because there is no absolute value. The results are interpretable only with respect to this test.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).