



Standard Terminology Relating to Catalysts and Catalysis¹

This standard is issued under the fixed designation D3766; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This terminology covers definitions of terms related to catalysts and catalysis.

NOTE 1—The Manual of Symbols and Terminology for Physicochemical Quantities and Units presents authoritative descriptions of many terms used in the field of catalysis.²

2. Terminology

2.1 Definitions:

activity, *n*—of a catalyst, the measure of the rate of a specific catalytic reaction conducted in the presence of a catalyst.

calcine, *v*—in catalysis, to heat a material to a high temperature causing a physical or chemical change, for example, loss of moisture and volatile matter, or a phase change, or both.

catalyst bed support, *n*—an essentially inert plate, grid, particulate bed, or other structural component designed to hold up or bear a quantity of catalyst in a catalytic reactor.

catalyst carrier, *n*—a solid, generally porous material upon the surface or into the voids of which catalytic materials are placed to create the desired catalyst.

DISCUSSION—A carrier may have or contribute to catalytic activity.

catalyst substrate, *n*—less preferred alternative term for **catalyst carrier**.

catalyst support, *n*—less preferred alternative term for **catalyst carrier**.

crush strength, *n*—in catalysis, a measure of the resistance of formed catalysts or catalyst carriers, either singly or in bulk, to loss of form when subjected to a compressive force.

DISCUSSION—Formed catalysts may include tablets, spheres, extrudates, rings, pellets, etc. and should be distinguished from powders and granules.

density, packing (bulk), *n*—the ratio of the mass of a collection of discrete pieces of solid material to the sum of the volumes of: the solids in each piece, the voids within the pieces, and the voids among the pieces of the particular collection.

density, particle (envelope), *n*—the ratio of the mass of a particle to the sum of the volumes of: the solid in each piece and the voids within each piece, that is, within close-fitting imaginary envelopes completely surrounding each piece.

density, skeletal, *n*—the ratio of the mass of discrete pieces of solid material to the sum of the volumes of: the solid material in the pieces and closed (or blind) pores within the pieces.

density, theoretical, *n*—the ratio of the mass of a collection of discrete pieces of solid material to the sum of the volumes of said pieces, the solid material having an ideal regular arrangement at the atomic level.

envelope, *n*—of a particle in catalysis, a theoretical surface that encloses the particle and that bridges openings to the interior of the particle.

pore, *n*—in catalysis, a small opening in a material permitting admission, adsorption, or passage of a fluid.

pore size distribution, *n*—in catalysis, the volume of pores of a material expressed or displayed as a function of pore diameters.

pore volume distribution, *n*—in catalysis, an alternative term for pore size distribution.

porosity, *n*—of particles in catalysis, the ratio of the volumes of the pores in the particles to the volumes enclosed by their envelopes.

selectivity, *n*—of a catalyst, the measure of the distribution of products in a specific reaction conducted in the presence of a catalyst.

sintering, *n*—in catalysis, a reduction of the surface area of a catalyst carrier or other solid catalytic material caused by heat.

DISCUSSION—Sintering may be enhanced by steam or other chemical species and may be accompanied by changes in crystallinity.

surface area, *n*—in catalysis, the measure of the total surface of a material per unit mass or volume.

DISCUSSION—This is usually expressed as m^2/g or m^2/cm^3 and is also sometimes called *specific surface area*.

¹ This terminology is under the jurisdiction of ASTM Committee D32 on Catalysts and is the direct responsibility of Subcommittee D32.92 on Nomenclature and Definitions.

Current edition approved April 1, 2008. Published April 2008. Originally approved in 1979. Last previous edition approved in 2007 as D3766–86(2007). DOI: 10.1520/D3766-08.

² “The Manual of Symbols and Terminology for Physicochemical Quantities and Units—Appendix II. Definitions, Terminology and Symbols in Colloid and Surface Chemistry. Part II: Heterogeneous Catalysis,” Pure and Applied Chemistry, Vol 46, No. 1, 73–90(1976).

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).